





TECHNICAL INFORMATION

FOR PROFESSIONAL USE ONLY

<h3>UBS ANTI-GRAVEL</h3> <p>CAR BODY PROTECTION AGENT</p>	
<p>PRODUCTS</p>	
<p>Troton UBS ANTI-GRAVEL 1 kg</p>	<p>COLOUR: black, grey, white</p>
<p>PRODUCT DESCRIPTION</p>	<p>GLOSS GRADE: matt</p>
<p>This product is designed to protect automotive bodywork from stone chips and the damaging effects of gasoline, oil, water, and salt. It creates a durable and flexible protective coating with a distinctive texture, offering soundproofing and sound-absorbing properties. It is free from bituminous substances and asphalt. It can be overcoated with any acrylic paints.</p> <ul style="list-style-type: none"> • Reduced VOC content. • Dust-free application. • High-quality synthetic resins ensure durability and resistance of the coating, even under tough conditions. 	

<p>VOLATILE ORGANIC COMPOUNDS</p>	
<p>VOC = 410 [g/l] These products meet the EU directive (2004/42/WE/II B) that sets the VOC value for its category (e), at 840 g/l.</p>	
<p>SURFACE PREPARATION</p>	
<p>The product has very good adhesion to various surfaces.</p> <p>It can be applied over:</p> <ul style="list-style-type: none"> • polyester laminates, • polyester putties, • epoxy primers, • 2K acrylic primers, • steel substrates, • stainless steel substrates, • zinc coated substrates, • aluminium substrates, • wash primers, • plastic. 	<p>Polyester laminates: should be degreased, dry sanded (P80-P120) and degreased again.</p> <p>Polyester putties: should be dry sanded (P120).</p> <p>Primers: should be degreased, dry sanded (P220-P280) and degreased again.</p> <p>Steel surfaces: should be degreased, dry sanded (P80-P120) and degreased again.</p> <p>Stainless steel: should be degreased.</p> <p>Aluminium and zinc surfaces: should be degreased, dulled with the abrasive cloth and degreased again.</p> <p>Old coats: should be degreased, dry sanded (P220-P280) and degreased again.</p> <p>Plastic surfaces: should be pre-washed with Silicone Remover Troton, scuffed with abrasive non-woven fabric, and degreased again. Due to the variety of plastics, an adhesion test should be performed.</p> <p>It is recommended to bake plastic panels at 50°C which helps to remove silicone from the surface.</p>

APPLICATION PROCESS			
	<p>USE</p> <p>Caution: <i>Shake before use!</i></p> <p>If applied directly on steel, it is recommended to apply top coat or enamel first.</p>		<p>NUMBER OF LAYERS AND SPRAY GUN PARAMETERS</p>
	<p>EVAPORATION TIME</p> <p>Between coats: approx. 10 min.</p>		<p>Using the UBS gun with a 4.0 mm nozzle (recommended air pressure 2-4 bar), apply two crossed coats.</p> <p>Apply at distance of 20 – 60 cm from surface.</p> <p>Number of layers: 2-3.</p> <p>Thickness of a single dry layer: approx. 100 µm.</p>
	<p>CURING TIME</p> <p>60 minutes at 20°C.</p> <p>Temperature below 20°C significantly increases the hardening time.</p>		<p>COATING</p> <p>Product is overpaintable after 1 hour from application.</p>

PRODUCT EFFICIENCY

The product packaging (1 kg) is sufficient to cover approximately 3.5 m² of dry layer with a thickness of 100 µm.

GENERAL NOTES

Caution: *To maintain safety, always follow the instructions given in the MSDS of the products.*

USE

1. Shake before use!
2. Apply 2 or 3 layers with intervals of no more than 10 minutes between each layer.

STORAGE

Store the product between 15 to 25°C in a sealed container, in dry and cool places, away from fire and heat sources, as well as direct sunlight.

Note: *After each use the container with product should be immediately closed!*

WARRANTY PERIOD

Troton UBS ANTI GRAVEL 1 kg - 24 months from the date of production

PRODUCT	Art. No.
Troton UBS ANTI-GRAVEL 1 kg	16689 (white); 16690 (black); 16691 (grey)

LIMITATION OF LIABILITY

The information contained in the TDS is up-to-date and correct on the day the information is released.

Because TROTON can not control or predict the conditions under which a product will be used, each user should review information in the specific context of the intended usage. To the maximum extent permitted by applicable law, TROTON shall not be liable for damages of any kind arising from the use or reliance on information contained in this TDS.

Given the variety of factors that can affect the usage and application of the TROTON product, some of which are only within the user's knowledge and control range, it is essential that the user evaluate the TROTON product to determine if the product is fit for a particular purpose and whether the product is suitable for the user's usage.

Under no circumstances shall TROTON be liable to the user or any third party for any indirect, derivative, incidental, special or punitive damages, including loss of profits resulting from the use of products manufactured by TROTON and / or TROTON's services.

All information are based upon the precise laboratory studies and many years of experience. The good market position does not release us from the constant supervision of our products quality. However, we are not responsible for the final effects of the improper storage or application of our products, as well as for work inconsistent with the good craft practice.

TROTON Sp. z o.o.
Ząbrowo, Poland.